



Flexaren 14006

CAS No.: 24937-78-8

Flexaren 14006

Flexaren 14006 is an ethylene vinyl acetate copolymer with 14% content of vinyl acetate. The product is manufactured by high pressure tubular process.

Flexaren 14006 is more elastic than LDPE, compatible with a wide range of polymers and can be processed with the same equipment.

Properties

- Outstanding flexibility (especially at low temperatures)

Applications

- Closure sealants
- Coating
- Masterbatches

Product Specification

	Value	Unit	Method
MFI (@ 190°C; 2.16kg)	6	g/10min	ISO 1133
Density (@ 20°C)	0.934	g/cm ³	DIN EN ISO 1183-1
VA content	14	%w/w	FTIR
Vicat-softening-temperature	62	°C	ISO 306 Method A
Hardness Shore A	91	-	ISO 868
Hardness Shore D	35	-	ISO 868
Strength (@ 50% elongation)	4.1	MPa	ISO 527 (PK 1 BA)
Tensile strength (@ break)	17	MPa	ISO 527 (PK 1 BA)
Elongation (@ break)	> 750	%	ISO 527 (PK 1 BA)
Processing recommendation	100 - 150	°C	-

The values listed are standard values.

Food Legislation

The monomers and other source materials used to produce commodities of Flexaren are mentioned in the EC directive 2002/72. According to this Flexaren has been approved for the manufacture of consumer goods which are used in contact with food, with a restriction being applicable to vinyl acetate (migration value SML=12 mg/kg).

Safety and Toxicology

Flexaren has not been classified as hazardous material in accordance with the Hazardous Material Act and does not require marking. Disposal of the product is to be carried out in accordance with the local regulations. For further information please see the relevant Safety Data Sheet at www.innospecinc.com

Packaging, Shipment and Storage

Flexaren is delivered as granular material of natural colouring, preferably packed in 25 kg LDPE-bags on lined pallets of 750 kg each or as loose material in bulk trucks. Other types of shipping and packaging upon inquiry. Flexaren shall be stored in its original packaging at room temperature at a dry place. Direct sun radiation and contact with water should be avoided.



For further information, please email your region:

america-ac@innospecinc.com, aspac-ac@innospecinc.com, emea-ac@innospecinc.com

www.innospecinc.com

Issue No. 3/2008

The facts stated and the recommendations made are based on our own research and/or the research of others, and are believed to be accurate. No guarantee of their accuracy is made, however, and unless otherwise expressly provided by law or in written contract, the materials are sold without warranties, expressed or implied, in particular without guarantee as to suitability for particular purpose. Innospec assumes no responsibility for injury or damage to users or third parties. Recipient agrees to assume all risk and liability whether used singly or in combination with other materials.